

MoldMAX LH[®]

Materion Brush Performance Alloys' MoldMAX LH (Low Hard) is a premium copper mold alloy that provides hardness and strength comparable with standard AISI P-20 tool steel and a thermal conductivity five-times higher. MoldMAX LH is used for injection mold cores and cavities where moderate hardness and high toughness and conductivity are required.

CHEMICAL COMPOSITION (weight percent)

Alloy	Beryllium	Cobalt	Copper
MoldMAX LH	1.6 – 2.0	0.2 – 0.3	Balance

PHYSICAL PROPERTIES

Elastic Modulus	Melting Point (Solidus)	Density	Thermal Expansion	Thermal Conductivity (100 °C)	Heat Capacity (100 °C)
19,000 ksi 131 GPa	~1600 °F ~870 °C	.302 lb/in ³ 8.36 g/cm ³	9.7x10 ⁻⁶ in/in °F 17.5 x 10 ⁻⁶ °C ⁻¹	90 BTU/hr·ft·°F 155 W/m·K	.10 BTU/lb·°F 0.44 J/g·K

TYPICAL MECHANICAL PROPERTIES*

0.2% Offset Yield Strength	Ultimate Tensile Strength	Fatigue Strength 10 ⁷ Cycles (R=-1)	Elongation	Impact Strength	Hardness
110 ksi 760 MPa	140 ksi 965 MPa	>45 ksi >310 MPa	15%	15 ft·lb 20 J	30 HRC

*Properties may vary by shape and thickness.

FORMS AVAILABLE

Rounds, square and rectangular bars, plate and forged rings.

RELATED INFORMATION

Additional information on MoldMAX products can be obtained by calling 800-375-4205.

SAFE HANDLING OF COPPER BERYLLIUM

Handling copper beryllium in solid form poses no special health risk. Like many industrial materials, beryllium-containing materials may pose a health risk if recommended safe handling practices are not followed. Inhalation of airborne beryllium may cause a serious lung disorder in susceptible individuals. The Occupational Safety and Health Administration (OSHA) has set mandatory limits on occupational respiratory exposures. Read and follow the guidance in the Material Safety Data Sheet (MSDS) before working with this material. For additional information on safe handling practices or technical data on copper beryllium, contact Materion Brush Performance Alloys, Technical Service Department at 1-800-375-4205.

North American Service Centers – Sales Inquiries

For strip, wire and rod under 0.4" (10 mm) diameter
Elmhurst, IL
TOLL FREE: 800.323.2438
LOCAL: +(1) 630.832.9650
FAX: +(1) 630.832.9657

For plate, tube, bar, and rod 0.4" (10 mm) diameter and over
Warren, MI
TOLL FREE: 800.521.8800
LOCAL: +(1) 586.772.2700
FAX: +(1) 586.772.2472

International Sales Offices

CHINA/HONG KONG
TEL: +852.2318.1960/1907
brushalloysHK-info@materion.com

INDIA/PUNE
TEL: +(91) 99606.33744
brushalloysIN-info@materion.com

SINGAPORE/ASEAN
TEL: +(65) 6842.4456
brushalloysSG-info@materion.com

CHINA/SHANGHAI
TEL: +(86) 21.5237.2328
brushalloysCN-info@materion.com

JAPAN
TEL: +(81) 33.230.2961
brushalloysJP-info@materion.com

TAIWAN, R.O.C.
TEL: +(886) 2.2747.8800x121
brushalloysTW-info@materion.com

GERMANY
TEL: +(49) 711.830.930
brushalloysDE-info@materion.com

REPUBLIC OF KOREA
TEL: +(82) 32.811.2171
brushalloysKR-info@materion.com

UNITED KINGDOM @ IRELAND
TEL: +(44) 118.930.3733
brushalloysUK-info@materion.com

To obtain a complete list of Materion's global distributor/agent network, visit us online at www.materion.com/BrushAlloys/ContactUs.



Materion Brush Performance Alloys
6070 Parkland Boulevard
Mayfield Heights, OH 44124 USA
phone: 216.486.4200 fax: 216.383.4005
email: BrushAlloys-info@materion.com

MATERION CORPORATION

www.materion.com/alloys

AD0059_0311

MoldMAX LH® is a Registered Trademark of Materion Brush Inc.
© 2011 Materion Brush Inc.