

PROtherm™

Materion Brush Performance Alloys' PROtherm™ is a high conductivity copper mold alloy with good strength. PROtherm™ is used as blow mold cavities, injection mold cores and cavities and hot runners. The alloy provides excellent toughness, and the highest conductivity of any alloy with tensile strength in excess of 100,000 psi.

CHEMICAL COMPOSITION (weight percent)

Alloy	Nickel	Beryllium	Copper
PROtherm™	1.4 – 2.2	0.2 – 0.6	Balance

PHYSICAL PROPERTIES

Elastic Modulus	Melting Point (Solidus)	Density	Thermal Expansion	Thermal Conductivity (100 °C)	Heat Capacity (100 °C)
20,000 ksi 138 GPa	1900 °F 1040 °C	.319 lb/in ³ 8.83 g/cm ³	9.8x10 ⁻⁶ in/in °F 1.8x 10 ⁻⁵ °C ⁻¹	145 BTU/hr ft ·°F 250 W/m ·K	.099 BTU/lb ·°F 0.41 J/g ·K

TYPICAL MECHANICAL PROPERTIES*

0.2% Offset Yield Strength	Ultimate Tensile Strength	Fatigue Strength 10 ⁷ Cycles (R=-1)	Elongation	Impact Strength	Hardness
90 ksi 620 MPa	105 ksi 725 MPa	35 ksi 240 MPa	15%	40 ft ·lb 55 J	20 HRC (97 HRB)

*Properties may vary by shape and thickness.

FORMS AVAILABLE

Rounds, square and rectangular bars, plate and forged rings.

RELATED INFORMATION

Additional information on PROtherm™ products can be obtained by calling 800-375-4205.

North American Service Centers – Sales Inquiries

For strip, wire and rod under 0.4" (10 mm) diameter

Elmhurst, IL

TOLL FREE: 800.323.2438
LOCAL: +(1) 630.832.9650
FAX: +(1) 630.832.9657

For plate, tube, bar, and rod 0.4" (10 mm) diameter and over

Warren, MI

TOLL FREE: 800.521.8800
LOCAL: +(1) 586.772.2700
FAX: +(1) 586.772.2472

International Sales Offices

CHINA/HONG KONG

TEL: +852.2318.1960/1907
brushalloysHK-info@materion.com

INDIA/PUNE

TEL: +(91) 99606.33744
brushalloysIN-info@materion.com

SINGAPORE/ASEAN

TEL: +(65) 6842.4456
brushalloysSG-info@materion.com

CHINA/SHANGHAI

TEL: +(86) 21.5237.2328
brushalloysCN-info@materion.com

JAPAN

TEL: +(81) 33.230.2961
brushalloysJP-info@materion.com

TAIWAN, R.O.C.

TEL: +(886) 2.2747.8800x121
brushalloysTW-info@materion.com

GERMANY

TEL: +(49) 711.830.930
brushalloysDE-info@materion.com

REPUBLIC OF KOREA

TEL: +(82) 32.811.2171
brushalloysKR-info@materion.com

UNITED KINGDOM @ IRELAND

TEL: +(44) 118.930.3733
brushalloysUK-info@materion.com

To obtain a complete list of Materion's global distributor/agent network, visit us online at www.materion.com/BrushAlloys/ContactUs.

Materion Brush Performance Alloys

6070 Parkland Boulevard
Mayfield Heights, OH 44124 USA
phone: 216.486.4200 fax: 216.383.4005
email: BrushAlloys-info@materion.com

MATERION CORPORATION

www.materion.com/alloys

AD0060_0311

© 2011 Materion Brush Inc.