

BrushForm® 158 Strip - TM16 Temper

Materion Performance Alloys' BrushForm® 158 Strip is a high-performance, heat treated spinodal copper nickel tin alloy designed to provide optimal formability and strength characteristics. TM16 provides excellent flatness and stiffness coupled with high resistance to vibration, fatigue and impact loading. This makes it ideal for voice coil motor springs in optical image stabilization systems.

CHEMICAL COMPOSITION (weight percent)

Alloy	Nickel	Tin	Copper
BrushForm® 158 Strip	14.5 - 15.5	7.5 - 8.5	Balance

PHYSICAL PROPERTIES

Elastic Modulus	Density	Typical Electrical Conductivity	Coefficient of Thermal Expansion	Relative Magnetic Permeability	Poisson's Ratio
128 GPa	9.00 g/cm ³	7% IACS 4 MS/m	16.4 ppm/°C	<1.01	0.3

MECHANICAL PROPERTIES

Temper	Data Type	0.2% Offset Yield Strength (MPa)	Ultimate Tensile Strength (MPa)	Elongation (%) *	Hardness (HV)
TM16	Specification Range	1365-1462	1400-1510	1.0 min.	375-450
	Design/Engineering Nominal Value	1413	455	1.5	400

* Percent elongation valid only for strip greater than 0.10 mm thick.

STANDARD AVAILABILITY

Mill Hardened Tempered Strip: 0.025 mm – 0.12mm gauge.

SPECIFICATIONS AND STANDARDS

UNS C72900, ASTM B740

North American Service Centers – Sales Inquiries

For strip ≤ 0.060 " (1.5 mm) thick, wire
and rod ≤ 0.5 " (12.7 mm) diameter:

Elmhurst, IL

TOLL FREE: 800-323-2438

PHONE: +(1) 630-832-9650

FAX: +(1) 630-832-9657

International Sales Offices

CHINA/HONG KONG

TEL: + (852) 2318-1960 / 1907

brushalloysHK-info@materion.com

CHINA/SHANGHAI

TEL: + (86) 21-5237-2328

brushalloysCN-info@materion.com

GERMANY

TEL: + (49) 711-830-930

brushalloysDE-info@materion.com

JAPAN

TEL: + (81) 33 230-2961

brushalloysJP-info@materion.com

REPUBLIC OF KOREA

TEL: + (82) 2 702-2961

brushalloysKR-info@materion.com

SINGAPORE/ASEAN

TEL: + (65) 6842-4456

brushalloysSG-info@materion.com

TAIWAN, R.O.C.

TEL: + (886) 2-2747-8800 x-121

brushalloysTW-info@materion.com

UNITED KINGDOM & IRELAND

TEL: + (44) 118-930-3733

brushalloysUK-info@materion.com

OTHER CONTACT INFORMATION

Technical Service	Properties, application and design assistance, fabrication and processing assistance, etc.	800-375-4205 +(1) 216-692-3108
International Sales	US distributors	
World-wide Distribution	International distributors	

Materion Brush Performance Alloys

6070 Parkland Boulevard
Mayfield Heights, OH 44124 USA
phone: 216.486.4200 fax: 216.383.4005
email: BrushAlloys-info@materion.com

MATERION CORPORATION

www.materion.com/alloys

AD0119_0817

BrushForm® is a Registered Trademark of Materion Brush Inc.
© 2016 Material Brush Inc.