

Alloy 25 (C17200) Strip

Materion Brush Performance Alloys' Alloy 25 strip provides the highest strength of any copper alloy, with electrical conductivity considerably greater than other high strength copper alloys. Since it is heat treated after forming, it provides excellent formability and ductility. This alloy features good stress relaxation resistance and high fatigue strength. Typical applications include pressure sensor bellows, burn-in and test socket contacts, computer processor socket contacts, and electromagnetic shielding gaskets.



CHEMICAL COMPOSITION (weight percent)

Alloy	Beryllium	Nickel + Cobalt	Nickel + Cobalt + Iron	Copper
C17200	1.80 – 2.00	0.2 min.	0.6 max.	Balance

PHYSICAL PROPERTIES*

Elastic Modulus	Melting Point (Solidus)	Electrical Conductivity/resistivity	Density**	Thermal Expansion Coefficient	Thermal Conductivity (25 °C)
19,000 ksi 131 GPa	1600°F 870 °C	22-28% IACS 6.2-7.8 μΩ-cm	0.302 lb/in ³ 8.36 g/cm ³	9.7x10 ⁻⁶ in/in °F 17.5x10 ⁻⁶ m/m °C	60 BTU/ft hr °F 105 W/ m K

*Properties specified for the precipitation age hardened (heat treated) condition

** Density in the cold-rolled condition (prior to heat treatment) is 0.300 lbs/in³ (8.30 g/cm³)

MECHANICAL PROPERTIES*

Temper**	0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation***	Hardness	Formability (Minimum Bend Radius to Thickness Ratio for a 90° Bend)****	
	ksi	MPa	ksi	MPa			Percent	DPH
A (TB00)	30-55	200-380	60-78	410-540	35-65	90-144	0.0	0.0
¼ H (TD01)	60-80	410-560	75-88	510-610	20-45	121-185	0.0	0.0
½ H (TD02)	75-95	510-660	85-100	580-690	12-30	176-216	0.5	1.0
H (TD04)	90-115	620-800	100-120	680-830	2-18	216-287	1.0	2.9
AT (TF00)	140-175	960-1210	165-195	1130-1350	3-15	353-413	-	-
¼ HT (TH01)	150-185	1030-1280	175-205	1200-1420	3-10	353-424	-	-
½ HT (TH02)	160-195	1100-1350	185-215	1270-1490	1-8	373-435	-	-
HT (TH04)	165-205	1130-1420	190-220	1310-1520	1-6	373-446	-	-

*Properties may vary by thickness. **Heat treatment temperature is 600°F (315°C). AT temper requires a 3 hour soak time at temperature, the other tempers require 2 hours. ***Elongation numbers valid only for strip greater than 0.004" (0.10 mm) thick. ****Formability numbers valid for strip 0.010" (0.25 mm) and thinner.

FORMS AVAILABLE

Alloy 25 strip is available in widths ranging from 0.050" to 16" (1.27 mm to 406.5 mm) and in thicknesses ranging from 0.002" to 0.188" (0.05 mm to 4.77 mm). It is also available in rod, wire, bar, plate, and tube.

SPECIFICATIONS AND STANDARDS

C17200, ASTM B-194, AMS 4530, AMS 4532, SAE J 461, SAE J 463, NACE MRO175/ISO 15156, QQC-533, JIS H3130, EN 1654, EN 13148, EN 14436

RELATED INFORMATION

Additional technical information on Alloy 25 strip may be obtained by phoning 800-375-4205. For pricing and availability, phone 800-323-2438, or the local sales number listed on the bottom of this datasheet.

SAFE HANDLING OF COPPER BERYLLIUM

Handling copper beryllium in solid form poses no special health risk. Like many industrial materials, beryllium-containing materials may pose a health risk if recommended safe handling practices are not followed. Inhalation of airborne beryllium may cause a serious lung disorder in susceptible individuals. The Occupational Safety and Health Administration (OSHA) has set mandatory limits on occupational respiratory exposures. Read and follow the guidance in the Safety Data Sheet (SDS) before working with this material. For additional information on safe handling practices or technical data on copper beryllium, contact Materion Performance Alloys, Technical Service Department at 1-800-375-4205.

TOLERANCES

Strip Thickness (inches)		Standard Thickness Tolerance (inches)	Strip Thickness (mm)		Standard Thickness Tolerance (mm)
Over	Including	Plus or Minus	Over	Including	Plus or Minus
	0.0020	0.00010		0.05	0.003
0.0020	0.0040	0.00015	0.05	0.10	0.004
0.0040	0.0060	0.00020	0.10	0.15	0.005
0.0060	0.0090	0.00025	0.15	0.20	0.006
0.0090	0.0130	0.00030	0.20	0.30	0.008
0.0130	0.0260	0.00040	0.30	0.70	0.010
0.0260	0.0370	0.00060	0.70	1.00	0.015
0.0370	0.0500	0.00080	1.00	1.30	0.020
0.0500	0.0750	0.00100	1.30	2.00	0.025

Additional tolerances are per ASTM B 194. Please specify the exact tolerances that you require when you place your order. Tighter tolerances may be available at additional cost. Please contact your local sales engineer to confirm the requested capability.

North American Service Centers – Sales Inquiries

For strip ≤ 0.060 " (1.5 mm) thick.
wire and rod ≤ 0.5 " (12.7 mm)
diameter:

Elmhurst, IL
TOLL FREE: 800-323-2438
PHONE: +(1) 630-832-9650
FAX: +(1) 630-832-9657

International Sales Offices

CHINA/HONG KONG

TEL: + (852) 2318-1960 / 1907
brushalloysHK-info@materion.com

JAPAN

TEL: + (81) 33 230 2961
brushalloysJP-info@materion.com

TAIWAN, R.O.C.

TEL: + (886) 2-2747-8800 x-121
brushalloysTW-info@materion.com

CHINA/SHANGHAI

TEL: + (86) 21-5237-2328
brushalloysCN-info@materion.com

REPUBLIC OF KOREA

TEL: + (82) 32-811-2171
brushalloysKR-info@materion.com

UNITED KINGDOM & IRELAND

TEL: + (44) 118-930-3733
brushalloysUK-info@materion.com

SINGAPORE/ASEAN

TEL: + (65) 6842-4456
brushalloysSG-info@materion.com

GERMANY

TEL: + (49) 71 1-830-930
brushalloysDE-info@materion.com