

Alloy 174 (C17410) Strip

Materion Performance Alloys' Alloy 174 strip is a mill hardened copper beryllium strip alloy designed for use in the Automotive, Appliance, and DataCom/TeleCom markets. It provides high yield and fatigue strength with high electrical conductivity and good resistance to stress relaxation. Typical applications include high reliability automotive terminals and spring contacts for switches and relays.



CHEMICAL COMPOSITION (weight percent)

Alloy	Beryllium	Cobalt	Copper
C17410	0.15-0.50	0.35-0.60	Balance

PHYSICAL PROPERTIES*

Elastic Modulus	Melting Point (Solidus)	Electrical Conductivity/ Resistivity	Density**	Thermal Expansion Coefficient	Thermal Conductivity (25 °C)
20,000 ksi 138 GPa	1880°F 1020 °C	45-60% IACS 2.9-3.8 μΩ-cm	0.318 lb/in ³ 8.80 g/cm ³	9.8x10 ⁻⁶ in/in °F 17.6x10 ⁻⁶ m/m °C	135 BTU/ft hr °F 230 W/ m K

*Properties specified for the precipitation age hardened (heat treated) condition

MECHANICAL PROPERTIES**

Temper***	0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation ***	Hardness	Formability (Minimum Bend Radius to Thickness Ratio for a 90° Bend)****	
	ksi	MPa	ksi	MPa			Percent	DPH
½ HT (TH02) HT (TH04)	80-100	550-690	95-115	665-790	10-20	180-230	0.5	0.5
	100-120	690-830	110-130	760-895	7-17	210-278	1.2	5.0

Properties may vary by thickness. *Percent elongation numbers are valid only for strip thicker than 0.004" (0.10 mm).

****Formability numbers valid for strip 0.010" (0.25 mm) and thinner.

Temper	10 ⁸ Cycle R=0 (Unidirectional) Fatigue Strength		10 ⁸ Cycle R=-1 (Fully Reversed) Fatigue Strength		1000 Hour Stress Relaxation Resistance*****		
	ksi	MPa	ksi	MPa	100°C	150°C	200°C
½ HT (TH02) HT (TH04)	75-85	515-585	35-45	240-310	94%	82%	64%
	85-95	585-655	55-65	380-450	95%	85%	77%

*****Stress remaining after 1000 hours exposure. Initial stress = 75% of the 0.2% offset yield strength

FORMS AVAILABLE

Alloy 174 mill hardened strip is available in widths ranging from 0.050" to 16" (1.27 mm to 406.5 mm) and in thicknesses ranging from 0.002" to 0.0787" (0.05 mm to 2.00 mm).

SPECIFICATIONS AND STANDARDS


C17410, ASTM B-768

RELATED INFORMATION

Additional technical information on Alloy 174 strip may be obtained by phoning 800-375-4205. For pricing and availability, phone 800-323-2438, or the local sales number listed on the back of this datasheet.

SAFE HANDLING OF COPPER BERYLLIUM

Handling copper beryllium in solid form poses no special health risk. Like many industrial materials, beryllium-containing materials may pose a health risk if recommended safe handling practices are not followed. Inhalation of airborne beryllium may cause a serious lung disorder in susceptible individuals. The Occupational Safety and Health Administration (OSHA) has set mandatory limits on occupational respiratory exposures. Read and follow the guidance in the Safety Data Sheet (SDS) before working with this material. For additional information on safe handling practices or technical data on copper beryllium, contact Materion Performance Alloys, Technical Service Department at 1-800-375-4205.



North American Service Centers – Sales Inquiries

For strip ≤ 0.060 " (1.5 mm) thick.
wire and rod ≤ 0.5 " (12.7 mm) diameter:

Elmhurst, IL

TOLL FREE: 800-323-2438

PHONE: +(1) 630-832-9650

FAX: +(1) 630-832-9657

International Sales Offices

CHINA/HONG KONG

TEL: + (852) 2318-1960 / 1907

brushalloysHK-info@materion.com

CHINA/SHANGHAI

TEL: + (86) 21-5237-2328

brushalloysCN-info@materion.com

GERMANY

TEL: + (49) 711-830-930

brushalloysDE-info@materion.com

JAPAN

TEL: + (81) 33 230 2961

brushalloysJP-info@materion.com

REPUBLIC OF KOREA

TEL: + (82) 32-811-2171

brushalloysKR-info@materion.com

SINGAPORE/ASEAN

TEL: + (65) 6842-4456

brushalloysSG-info@materion.com

TAIWAN, R.O.C.

TEL: + (886) 2-2747-8800 x-121

brushalloysTW-info@materion.com

UNITED KINGDOM & IRELAND

TEL: + (44) 118-930-3733

brushalloysUK-info@materion.com

Materion Performance Alloys

6070 Parkland Boulevard
Mayfield Heights, OH 44124 USA
phone: 216.383.6800 fax: 216.383.4005
email: BrushAlloys-info@materion.com

MATERION CORPORATION

www.materion.com/alloys

AD0070_0817

© 2017 Materion Brush Inc.