

## MoldMAX V®

Materion Performance Alloys' MoldMAX V (MMV) Alloy is a high conductivity, moderately high strength, copper nickel silicon chromium alloy. Applications include injection mold and blow mold cores and cavities.



### CHEMICAL COMPOSITION (weight percent)

Alloy	Nickel	Silicon	Chromium	Copper
MoldMAX V	6.4 – 7.6	1.5 – 2.5	0.6 – 1.2	Balance

### PHYSICAL PROPERTIES

Elastic Modulus	Melting Point (Solidus)	Density	Thermal Expansion	Thermal Conductivity (typical @100 °C)	Heat Capacity (typical @100 °C)
18,500 ksi 130 GPa	~1800 °F ~980 °C	.314 lb/in <sup>3</sup> 8.69 g/cm <sup>3</sup>	9.72x10 <sup>-6</sup> in/in °F 17.5 x 10 <sup>-6</sup> °C <sup>-1</sup>	92 BTU/hr ft °F 160 W/m °C	0.098 BTU/lb °F 0.41 J/g °C

### MECHANICAL PROPERTIES\*

Product Size Range	Typical Minimum 0.2% Offset Yield Strength	Typical Min. Ultimate Tensile Strength	Typical Fatigue Strength 10 <sup>7</sup> Cycles (R = -1)	Typical Minimum Elongation	Typical Impact Strength	Minimum Hardness
Rod 0.5 – 3.5 in. 12.5 – 89 mm	115 ksi 790 MPa	125 ksi 860 MPa	40 ksi 275 MPa	7%	5 ft lb 7 J	265 HBW (27 HRC)
Rod 4 – 5 in. 100 –125 mm	105 ksi 725 MPa	115 ksi 790 MPa	40 ksi 275 MPa	5%	5 ft lb 7 J	250 HBW (25 HRC)
Plate 0.5 – 2.5 in. 12.5 – 63.5 mm	100 ksi 690 MPa	115 ksi 790 MPa	40 ksi 275 MPa	5%	5 ft lb 7 J	250 HBW (25 HRC)

\*Hardness is tested via Brinell Test Method at 3000 kgf load and equivalent HRC values converted per ASTM-E-140, Table I Properties may vary by shape and thickness.

### FORMS AVAILABLE

Rounds, plates, and parts finished machined per customer drawings.

### RELATED INFORMATION

Additional technical information on MoldMAX® products can be obtained by visiting [www.MoldMax.com](http://www.MoldMax.com) or by calling 800-375-4205 (USA). For pricing and availability in North America, contact the sales location.

## North American Service Centers – Sales Inquiries

For bar, tube, plate/sheet >0.060" (1.5 mm) thick  
and rod >0.5" (12.7 mm) diameter:

### Warren, MI

TOLL FREE: 800-521-8800

PHONE: +(1) 586-772-2700

FAX: +(1) 586-772-2472

## International Sales Offices

### CHINA/HONG KONG

TEL: + (852) 2318-1960 / 1907

[brushalloysHK-info@materion.com](mailto:brushalloysHK-info@materion.com)

### JAPAN

TEL: + (81) 33 230 2961

[brushalloysJP-info@materion.com](mailto:brushalloysJP-info@materion.com)

### TAIWAN, R.O.C.

TEL: + (886) 2-2747-8800 x-121

[brushalloysTW-info@materion.com](mailto:brushalloysTW-info@materion.com)

### CHINA/SHANGHAI

TEL: + (86) 21-5237-2328

[brushalloysCN-info@materion.com](mailto:brushalloysCN-info@materion.com)

### REPUBLIC OF KOREA

TEL: + (82) 32-811-2171

[brushalloysKR-info@materion.com](mailto:brushalloysKR-info@materion.com)

### UNITED KINGDOM & IRELAND

TEL: + (44) 118-930-3733

[brushalloysUK-info@materion.com](mailto:brushalloysUK-info@materion.com)

### GERMANY

TEL: + (49) 711-830-930

[brushalloysDE-info@materion.com](mailto:brushalloysDE-info@materion.com)

### SINGAPORE/ASEAN

TEL: + (65) 6842-4456

[brushalloysSG-info@materion.com](mailto:brushalloysSG-info@materion.com)



### Materion Performance Alloys

6070 Parkland Boulevard  
Mayfield Heights, OH 44124 USA  
phone: 216.486.4200 fax:216.383.4005  
email: [BrushAlloys-info@materion.com](mailto:BrushAlloys-info@materion.com)

### MATERION CORPORATION

[www.materion.com/alloys](http://www.materion.com/alloys)

**AD0056\_0817**

MoldMAX V® is a Registered Trademark of Materion Brush Inc.  
© 2017 Materion Brush Inc.