

MoldMAX HH® Alloy

Materion Performance Alloys' MoldMAX HH (High Hard) Alloy is the premier copper mold alloy. This alloy has a hardness and strength comparable with standard tool steels but its thermal conductivity is at four to six times higher. MoldMAX HH Alloy is used for injection mold cores and cavities and blow mold pinch-offs. Its high hardness provides durability in applications where other high conductivity copper alloys fail. The alloy resists galling against other mold alloys, including itself.

CHEMICAL COMPOSITION (weight percent)

Alloy	Beryllium	Cobalt	Copper
MoldMAX HH Alloy	1.6 – 2.0	0.2 – 0.3	Balance

PHYSICAL PROPERTIES

Elastic Modulus	Melting Point (Solidus)	Density	Thermal Expansion	Thermal Conductivity (100 °C)	Heat Capacity (100 °C)
19,000 ksi 131 GPa	~1600 °F ~870 °C	0.302 lb/in ³ 8.36 g/cm ³	9.7x10 ⁻⁶ in/in °F 17.5 x 10 ⁻⁶ °C ⁻¹	75 BTU/hr ft °F 130 W/m °C	0.10 BTU/lb °F 0.42 J/g °C

TYPICAL MECHANICAL PROPERTIES*

0.2% Offset Yield Strength	Ultimate Tensile Strength	Fatigue Strength 10 ⁷ Cycles (R=-1)	Elongation	Impact Strength	Hardness
145 ksi 1000 MPa	170 ksi 1170 MPa	>45 ksi >310 MPa	5%	5 ft ·lb 7 J	40 HRC

*Properties may vary by shape and thickness.

FORMS AVAILABLE

Rounds, square and rectangular bars, plate and forged rings.

RELATED INFORMATION

Additional technical information on MoldMAX® products can be obtained by visiting www.MoldMax.com or by calling 800-375-4205 (USA). For pricing and availability in North America, contact a sales location.

SAFE HANDLING OF COPPER BERYLLIUM

Handling copper beryllium in solid form poses no special health risk. Like many industrial materials, beryllium-containing materials may pose a health risk if recommended safe handling practices are not followed. Inhalation of airborne beryllium may cause a serious lung disorder in susceptible individuals. The Occupational Safety and Health Administration (OSHA) has set mandatory limits on occupational respiratory exposures. Read and follow the guidance in the Safety Data Sheet (SDS) before working with this material. For additional information on safe handling practices or technical data on copper beryllium, contact Materion Performance Alloys, Technical Service Department at 1-800-375-4205.

North American Service Centers – Sales Inquiries

For bar, tube, plate/sheet >0.060” (1.5 mm) thick
and rod >0.5” (12.7 mm) diameter:

Warren, MI

TOLL FREE: 800-521-8800

PHONE: +(1) 586-772-2700

FAX: +(1) 586-772-2472

International Sales Offices

CHINA/HONG KONG

TEL: + (852) 2318-1960 / 1907

brushalloysHK-info@materion.com

JAPAN

TEL: + (81) 33 230 2961

brushalloysJP-info@materion.com

TAIWAN, R.O.C.

TEL: + (886) 2-2747-8800 x-121

brushalloysTW-info@materion.com

CHINA/SHANGHAI

TEL: + (86) 21-5237-2328

brushalloysCN-info@materion.com

REPUBLIC OF KOREA

TEL: + (82) 32-811-2171

brushalloysKR-info@materion.com

UNITED KINGDOM & IRELAND

TEL: + (44) 118-930-3733

brushalloysUK-info@materion.com

GERMANY

TEL: + (49) 711-830-930

brushalloysDE-info@materion.com

SINGAPORE/ASEAN

TEL: + (65) 6842-4456

brushalloysSG-info@materion.com



Materion Performance Alloys

6070 Parkland Boulevard
Mayfield Heights, OH 44124 USA
phone: 216.383.6800 fax:216.383.4005
email: BrushAlloys-info@materion.com

MATERION CORPORATION

www.materion.com/alloys

AD0057_0817

MoldMAX HH® is a Registered Trademark of Materion Brush Inc.
© 2017 Materion Brush Inc.