

## MoldMAX HH® Alloy

Materion Performance Alloys' MoldMAX HH (High Hard) Alloy is the premier copper mold alloy. This alloy has a hardness and strength comparable with standard tool steels but its thermal conductivity is at four to six times higher. MoldMAX HH Alloy is used for injection mold cores and cavities and blow mold pinch-offs. Its high hardness provides durability in applications where other high conductivity copper alloys fail. The alloy resists galling against other mold alloys, including itself.

### CHEMICAL COMPOSITION (weight percent)

| Alloy            | Beryllium | Cobalt    | Copper  |
|------------------|-----------|-----------|---------|
| MoldMAX HH Alloy | 1.6 – 2.0 | 0.2 – 0.3 | Balance |

### PHYSICAL PROPERTIES

| Elastic Modulus       | Melting Point (Solidus) | Density  | Thermal Expansion   | Thermal Conductivity (100 °C) | Heat Capacity (100 °C)        |
|-----------------------|-------------------------|--|---|-------------------------------|-------------------------------|
| 19,000 ksi<br>131 GPa | ~1600 °F<br>~870 °C     | 0.302 lb/in <sup>3</sup><br>8.36 g/cm <sup>3</sup> | 9.7x10 <sup>-6</sup> in/in °F<br>17.5 x 10 <sup>-6</sup> °C <sup>-1</sup> | 75 BTU/hr ft °F<br>130 W/m °C | 0.10 BTU/lb °F<br>0.42 J/g °C |

### TYPICAL MECHANICAL PROPERTIES\*

| 0.2% Offset Yield Strength | Ultimate Tensile Strength | Fatigue Strength 10 <sup>7</sup> Cycles (R=-1) | Elongation | Impact Strength | Hardness |
|----------------------------|---------------------------|--|------------|-----------------|----------|
| 145 ksi<br>1000 MPa        | 170 ksi<br>1170 MPa       | >45 ksi<br>>310 MPa                            | 5%         | 5 ft ·lb<br>7 J | 40 HRC   |

\*Properties may vary by shape and thickness.

### FORMS AVAILABLE

Rounds, square and rectangular bars, plate and forged rings.

### RELATED INFORMATION

Additional technical information on MoldMAX® products can be obtained by visiting [www.MoldMax.com](http://www.MoldMax.com) or by calling 800-375-4205 (USA). For pricing and availability in North America, contact a sales location.

## SAFE HANDLING OF COPPER BERYLLIUM

Handling copper beryllium in solid form poses no special health risk. Like many industrial materials, beryllium-containing materials may pose a health risk if recommended safe handling practices are not followed. Inhalation of airborne beryllium may cause a serious lung disorder in susceptible individuals. The Occupational Safety and Health Administration (OSHA) has set mandatory limits on occupational respiratory exposures. Read and follow the guidance in the Safety Data Sheet (SDS) before working with this material. For additional information on safe handling practices or technical data on copper beryllium, contact Materion Performance Alloys, Technical Service Department at 1-800-375-4205.

### North American Service Centers – Sales Inquiries

For bar, tube, plate/sheet >0.060” (1.5 mm) thick  
and rod >0.5” (12.7 mm) diameter:

#### Warren, MI

TOLL FREE: 800-521-8800

PHONE: +(1) 586-772-2700

FAX: +(1) 586-772-2472

### International Sales Offices

#### CHINA/HONG KONG

TEL: + (852) 2318-1960 / 1907

[brushalloysHK-info@materion.com](mailto:brushalloysHK-info@materion.com)

#### JAPAN

TEL: + (81) 33 230 2961

[brushalloysJP-info@materion.com](mailto:brushalloysJP-info@materion.com)

#### TAIWAN, R.O.C.

TEL: + (886) 2-2747-8800 x-121

[brushalloysTW-info@materion.com](mailto:brushalloysTW-info@materion.com)

#### CHINA/SHANGHAI

TEL: + (86) 21-5237-2328

[brushalloysCN-info@materion.com](mailto:brushalloysCN-info@materion.com)

#### REPUBLIC OF KOREA

TEL: + (82) 32-811-2171

[brushalloysKR-info@materion.com](mailto:brushalloysKR-info@materion.com)

#### UNITED KINGDOM & IRELAND

TEL: + (44) 118-930-3733

[brushalloysUK-info@materion.com](mailto:brushalloysUK-info@materion.com)

#### GERMANY

TEL: + (49) 711-830-930

[brushalloysDE-info@materion.com](mailto:brushalloysDE-info@materion.com)

#### SINGAPORE/ASEAN

TEL: + (65) 6842-4456

[brushalloysSG-info@materion.com](mailto:brushalloysSG-info@materion.com)



#### Materion Performance Alloys

6070 Parkland Boulevard  
Mayfield Heights, OH 44124 USA  
phone: 216.383.6800 fax:216.383.4005  
email: [BrushAlloys-info@materion.com](mailto:BrushAlloys-info@materion.com)

#### MATERION CORPORATION

[www.materion.com/alloys](http://www.materion.com/alloys)

AD0057\_0817

MoldMAX HH® is a Registered Trademark of Materion Brush Inc.  
© 2017 Materion Brush Inc.