

## MoldMAX V®

Materion's MoldMAX V (MMV) Alloy is a high conductivity, moderately high strength, copper nickel silicon chromium alloy. Applications include injection mold and blow mold cores and cavities.

### CHEMICAL COMPOSITION (WEIGHT PERCENT)

Alloy	Nickel	Silicon	Chromium	Copper
MoldMAX V	6.4 – 7.6	1.5 – 2.5	0.6 – 1.2	Balance

### PHYSICAL PROPERTIES

Elastic Modulus	Melting Point (Solidus)	Density	Thermal Expansion	Thermal Conductivity (typical @100 °C)	Heat Capacity (typical @100 °C)
18,500 ksi 130 GPa	~1800 °F ~980 °C	.314 lb/in <sup>3</sup> 8.69 g/cm <sup>3</sup>	9.72x10 <sup>-6</sup> in/in °F 17.5 x 10 <sup>-6</sup> °C <sup>-1</sup>	92 BTU/hr·ft·°F 160 W/m·°C	0.098 BTU/lb·°F 0.41 J/g·°C

### MECHANICAL PROPERTIES\*

Product Size Range	Typical Minimum 0.2% Offset Yield Strength	Typical Min. Ultimate Tensile Strength	Typical Fatigue Strength 107 Cycles (R = -1)	Typical Minimum Elongation	Typical Impact Strength	Minimum Hardness
Rod 0.5 - 3.5 in. 12.5 - 89 mm	115 ksi 790 MPa	125 ksi 860 MPa	40 ksi 275 MPa	7%	5 ft·lb 7 J	265 HBW (27 HRC)

\*Hardness is tested via Brinell Test Method at 3000 kgf load and equivalent HRC values converted per ASTM-E-140, Table 1 Properties may vary by shape and thickness.

### FORMS AVAILABLE

Rounds, plates, and parts finished machined per customer drawings.

### RELATED INFORMATION

Additional technical information on MoldMAX® products can be obtained by visiting [www.MoldMax.com](http://www.MoldMax.com) or by calling 800-375-4205 (USA). For pricing and availability in North America, contact the sales location.

Disclaimer:  
Only the buyer can determine the appropriateness of any processing practice, end-product or application. Materion does not make any warranty regarding its recommendations, the suitability of Materion's product, or its processing suggestions for buyer's end product, application or equipment.

The properties presented on this data sheet are for reference purposes only, intended only to initiate the material selection process. They do not constitute, nor are they intended to constitute, a material specification. Material will be produced to one of the applicable industry standards, if any, listed in the Industry Standards and Specification section.

Actual properties may vary by thickness and/or part number. Please contact your local sales engineer for detailed properties to be used in simulation.

Any properties marked as preliminary are subject to change at any time as the manufacturing process is further refined.