

## ToughMet® 3 AT Alloy Rod, Tube & Forged Rings Data Sheet

Materion's ToughMet 3 AT alloy is a wrought, spinodally hardened copper alloy engineered for high strength and hardness. It resists mechanical wear, galling, stress relaxation, corrosion and erosion. ToughMet 3 alloy retains its strength at elevated temperature. It is non-magnetic and easy to machine into complex components.

### CHEMICAL COMPOSITION (WEIGHT PERCENT)

Nickel	Tin	Copper
15	8	Balance

### PHYSICAL PROPERTIES

Elastic Modulus	Poisson's Ratio	Electrical Conductivity	Thermal Conductivity	Coefficient of Thermal Expansion	Density	Magnetic Permeability
21 x 10 <sup>6</sup> psi 144 kN/mm <sup>2</sup>	0.33	< 7% IACS < 4 MS/m	22 Btu/ft/hr/°F 38 W/m/°C	9.1 x 10 <sup>-6</sup> in/in/°F 16.6 x 10 <sup>-6</sup> m/m/°C	0.325 lb/in <sup>3</sup> 9.00 g/cm <sup>3</sup>	< 1.001

### MINIMUM MECHANICAL PROPERTIES

Form	Temper	Diameter		0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation % (in 4D)	Hardness HRC
		Inch	mm	ksi	N/mm <sup>2</sup>	ksi	N/mm <sup>2</sup>		
Rod	AT90	1 - 3.9	25.4 - 101.5	90	620	110	760	15	26
		4 - 9	101.6 - 228.6	90	620	110	760	12	26
	AT110	0.500 - 3.9	15.1 - 101.5	110	760	132	910	10	30
		4 - 9	101.6 - 228.6	110	760	127	875	6	30
Tube	AT90	1.625 - 3.9	41 - 101.5	90	620	110	760	15	22
		4 - 6.4	101.6 - 164	90	620	110	760	12	22
		6.5 - 8	165 - 203	90	620	110	760	12	22
	AT110	1.625 - 3.9	41 - 101.5	110	760	130	895	10	30
		4 - 7.9	101.6 - 203	110	760	130	895	6	30
		8 - 13	203.2 - 330	110	760	130	895	5	30
Rings	AT	15 - 80	380 - 2032	105	724	110	758	4	28

## STANDARD TOLERANCES ROD

Form	Temper	Diameter		Diameter Tolerance <sup>2</sup>		Length <sup>1</sup>	
		inch	mm	inch	mm	inch	mm
Rod	AT90, AT110	0.500 - 1	15.1 - 25	+ 0.040/-0	+ 1.0 /-0	72 - 162	1829 - 4115
		1.1 - 2	26 - 50	+ 0.060/-0	+ 0.1.5/-0		
		2.1 - 3	51 - 75	+ 0.100/-0	+ 2.5/-0		
		3.1 - 3.5	76 - 90	+ 0.140/-0	+ 3.5/-0		
		3.6 - 4	91 - 100	+ 0.240/-0	+ 6.0/-0		
		4.1 - 9	101 - 229	+ 0.240/-0	+ 6.0/-0		

## STANDARD TOLERANCES TUBE

Form	Temper	Outside Diameter		Inner Diameter		Diameter Tolerance <sup>2</sup>		Length <sup>1</sup>	
		inch	mm	inch	mm	inch	mm	inch	mm
Tube	AT90	1.625 - 2.5	41 - 63.5	Wall Thickness 10-20% of Outside Diameter <sup>4</sup>		+/- 0.030	+/- 0.75	72 - 162	1829 - 4115
		2.6 - 8	64 - 203			+/- 0.060	+/- 0.1.50		
	AT110	1.625 - 2.5	41 - 63.5			+/- 0.030	+/- 0.75		
		2.6 - 7.9	64 - 203			+/- 0.060	+/- 0.1.50		
		8 - 13	203 - 330			+/- 0.060	+/- 0.1.50		
Ring <sup>3</sup>	AT	15 - 80	380 - 2032	13 min	330 min	Machined Tolerance		9 max	229 max

1. Check with mill for special length requests
2. Check with mill for tighter tolerance
3. Rings are constrained by a 10,000 lb (4535 kg) maximum weight
4. This is just a guideline. Check with mill if this does not meet your requirement

## SURFACE AND FINISHING

Surface: Mill hardened finish.

## INDUSTRY STANDARDS AND SPECIFICATIONS

UNS C72900, AMS 4596, AMS4598

### Disclaimer:

Only the buyer can determine the appropriateness of any processing practice, end-product or application. Materion does not make any warranty regarding its recommendations, the suitability of Materion's product, or its processing suggestions for buyer's end product, application or equipment.

The properties presented on this data sheet are for reference purposes only, intended only to initiate the material selection process. They do not constitute, nor are they intended to constitute, a material specification. Material will be produced to one of the applicable industry standards, if any, listed in the Industry Standards and Specification section.

Actual properties may vary by thickness and/or part number. Please contact your local sales engineer for detailed properties to be used in simulation.

Any properties marked as preliminary are subject to change at any time as the manufacturing process is further refined.