



Issue No. 42 – June 2012

Updated from Original December 2002 Publication

## Summary of Electrical Contact Coatings

**Auld Lange Syne** - A review of the electrical contact materials discussed the previous 12 months.

- **Tin**
- **Tin-lead**
- **Nickel**
- **Gold**
- **Silver**
- **Platinum**
- **Palladium**

Editor's note: This issue was originally released at the end of 2002, which had been a very challenging year. The opening paragraph originally provided wishes for a more prosperous year in 2003. This issue will summarize all that was originally discussed in 2002 regarding contact coatings, and should make a handy reference.

**Tin** coatings are soft and easily solderable. They have the advantage of being much less expensive than all the other coatings. However, they are subject to fretting corrosion. This means that high contact forces are required (100-200 grams), and they must be used with lubricant. Wiping action is required during contact mating to disrupt any surface films. If the tin is applied by electroplating, it must be reflowed later to prevent tin whisker growth. Tin has a tendency to form a brittle intermetallic phase with copper, so a nickel underplate is recommended. Tin usually is limited to a maximum service temperature of 100 to 150 °C. Tin-based coatings should not be mated to precious metal, and they should not be used in contacts where there is a potential for arcing.

**Tin-lead** coatings are usually used for areas that will be soldered. They are immune to whisker growth, so reflow is not necessary. There also are many other compositions of tin-based solders, and new lead-free solders always are being developed.

**Nickel** is usually used as an undercoating for other metals like gold, tin or palladium. It acts as a barrier layer to prevent diffusion of the base metal to the surface. In the case of tin-coated contacts, it prevents the formation of copper-tin intermetallics. It passivates pores and bare edges, reducing the potential of pore corrosion and creep corrosion. Electroless nickel is a very hard and wear resistant coating. When used without a precious metal overplate, nickel is susceptible to fretting corrosion and requires a minimum contact force of approximately 200 grams.

**Gold** is a soft, inert, low friction, high conductivity coating. It has exceptional corrosion resistance, and requires little more than 15-35 grams of contact force. However, it wears easily, and does not solder well. It is often used in low current or high reliability applications. Gold should be limited to cases where the temperature does not exceed 125°C. Hard gold is more lubricious and wear resistant, although it is less conductive. Contacts plated with hard gold require a little more normal force, usually 35-50 grams. Both types of gold require a nickel underplate to act as a diffusion barrier.

**Silver** is the highest conductivity contact metal. It is used in high current applications where there may be a potential for minor arcing to occur. Silver can be used in applications where the temperature can reach 200°C. Even though it does not oxidize readily, it can still tarnish easily in the presence of chlorine, sulfur, etc. A contact force of 100-200 grams should be sufficient to disrupt any such films.

Silver composites and silver metal oxides are used in higher current, higher voltage switches where there is a potential for severe damage from arcing. They are more resistant to arc erosion

*The next issue of Technical Tidbits is a reprint of an introduction for Materion's 390®.*

## The Effects of Arcing (continued)

than plain silver. Their higher melting temperatures also make them more resistant to contact welding during make and break operations.

**Platinum** and **palladium** are currently very expensive contact materials. They are resistant to most forms of corrosion, although their surfaces can readily adsorb organic material from the environment, which creates a brown, powdery organic film. Both platinum and palladium are more resistant to wear than gold. They are often used in high reliability contacts where gold would wear away too quickly. A thin gold flash may be placed on the surface to reduce the potential for the formation of frictional polymer. A normal force of 50 to 100 grams is recommended for both platinum and palladium. It should be noted that these two metals also require a nickel underplate as a diffusion barrier.

Palladium nickel and palladium cobalt alloys are much more wear resistant than pure palladium. They may be used in sliding switch applications. Palladium silver is used in switching applications where arcing may be a concern.

The important point in all of this is that the individual application really drives the choice of coating method and material. The right choice of coating depends upon the ambient temperature, environmental contaminants present, current levels and number of mating cycles (not to mention cost.) The choice of plating material then dictates the normal force requirements.

In general, high normal force means more reliable contact. This does, however, mean that the insertion force will be high as well. Contacts are continually shrinking in size, requiring higher stress levels to achieve the required contact force. Furthermore, normal force tends to drop over time due to stress relaxation. In order to ensure adequate normal force at the end of life, the designed normal force will have to be increased above the bare minimum, which further increases both the stress and insertion force. These considerations will then go into the choice of the high performance base metal.

The optimal base material will be one that has high strength and good formability to allow for miniaturization. It will have good stress relaxation resistance to maximize normal force while minimizing insertion force. It will have good conductivity to minimize resistance. In highly cycled switch applications, it also will need to have good fatigue strength. Brush Wellman's copper beryllium alloys such as Alloy 25 (C17200) and Alloy Brush 60® (C17460) have the necessary properties to rise up to meet these challenges.

*Written by Mike Gedeon of Materion Brush Performance Alloys Customer Technical Service Department. Mr. Gedeon's primary focus is on electronic strip for the telecommunications and computer markets with emphasis on Finite Element Analysis (FEA) and material selection.*

## TECHNICAL TIDBITS

Materion Brush Performance Alloys  
6070 Parkland Blvd.  
Mayfield Heights, OH 44124  
(216) 486-4200  
(216) 383-4005 Fax  
(800) 375-4205 Technical Service



MATERION

### Reference:

### Technical Tidbits Issues 31 through 41

Please contact your local sales representative for further information on coating materials or other questions pertaining to Materion or our products.

### Health and Safety

Handling copper beryllium in solid form poses no special health risk. Like many industrial materials, beryllium-containing materials may pose a health risk if recommended safe handling practices are not followed. Inhalation of airborne beryllium may cause a serious lung disorder in susceptible individuals. The Occupational Safety and Health Administration (OSHA) has set mandatory limits on occupational respiratory exposures. Read and follow the guidance in the Material Safety Data Sheet (MSDS) before working with this material. For additional information on safe handling practices or technical data on copper beryllium, contact Materion Brush Performance Alloys