

ToughMet® 2 CX Tempers Rod, Tube & Plate

ToughMet 2 alloy is Materion's solution to your severe service material problems. By applying our proprietary technology process to produce the EquaCast® microstructure, tailored alloying additions and spinodal hardening technology, we have engineered ToughMet alloy to provide attributes beyond those typically found in a high-strength copper alloy. ToughMet 2 alloy in the cast and spinodally hardened (CX) condition exhibits tensile strength in excess of 105 ksi and hardness exceeding HRC 27 with excellent machinability. This Copper-9Nickel-6Tin alloy combines low coefficient of friction with wear resistance.

- Exceptional resistance to corrosion and cavitation
- Outstanding lubricity and durability in demanding applications
- Highly uniform composition in all product forms
- Available in a wide range of continuous-cast shapes and sizes

Physical Properties

Young Modulus	Poisson's Ratio	Electrical Conductivity	Thermal Conductivity	CTE (70 - 215°F) (20 - 100°C)	Density	Fatigue Limit (estimated)	Magnetic Permeability
17 x 10 ⁶ psi (117 GPa)	0.3	13 - 14% IACS	30 Btu/ft/hr/°F (52 W/m/°C)	9.0 x 10 ⁻⁶ /°F (16.2 x 10 ⁻⁶ /°C)	0.322 lb/in ³ (8.91g/cm ³)	20 ksi (138 MPa) at R=-1*	< 1.001

*Fatigue at 10⁶ cycles

Mechanical Properties

Temper	0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation	Hardness
	ksi	MPa	ksi	MPa	%	HRC
T2 CX90	90	621	105	724	3	27

Minimum values

Standard Availability

Plate: Thicknesses from $\frac{3}{4}$ to 12" (19 – 305 mm), width up to 20" (508 mm), lengths up to 60" (1.52 m).

Rod: Diameter from 2 to 12" inches (51 – 305 mm), in lengths up to 12 ft (3.66 m).

Tube: Outside diameter from 1 to 15" (25 – 381 mm), wall thicknesses approximately 10-12% of the outside diameter.

Industry Standards and Specifications

ASTM B505, UNS C96970

Related Information

Additional technical information on ToughMet 2 rod, tube or plate can be obtained by calling 800-375-4205. For pricing and availability, phone 800-521-8800.

Disclaimer:

Only the buyer can determine the appropriateness of any processing practice, end-product or application. Materion does not make any warranty regarding its recommendations, the suitability of Materion's product, or its processing suggestions for buyer's end product, application or equipment.

The properties presented on this data sheet are for reference purposes only, intended only to initiate the material selection process. They do not constitute, nor are they intended to constitute, a material specification. Material will be produced to one of the applicable industry standards, if any, listed in the Industry Standards and Specification section.

Actual properties may vary by thickness and/or part number. Please contact your local sales engineer for detailed properties to be used in simulation.

Any properties marked as preliminary are subject to change at any time as the manufacturing process is further refined.

MATERION Alloys and Composites

6070 Parkland Boulevard
Mayfield Heights, OH 44124 USA

Contact Us:

[materion.com/ContactPAC](https://www.materion.com/ContactPAC)
+1.800.375.4205

MATERION Global Headquarters

6070 Parkland Boulevard
Mayfield Heights, OH 44124 USA

DS-AM-248 © 2021 Materion Corporation