



BERYLLIUM SULFATE (BeSO₄·4H₂O) HIGH PURITY

Effective March 8, 2011

Rev B

	% (COMMODITY BASIS)	
Beryllium	5.0	Minimum
Beryllium Oxide Equivalent	13.8	Minimum
BeSO ₄ ·4H ₂ O	98.0	Minimum
Aluminum	.0007 Maximum or 140 ppm (Be Basis)	
Iron	.0007 Maximum or 140 ppm (Be Basis)	
Calcium	.0007 Maximum or 140 ppm (Be Basis)	
Chromium	.0002 Maximum or 40 ppm (Be Basis)	
Copper	.0001 Maximum or 20 ppm (Be Basis)	
Lithium	.0001 Maximum or 20 ppm (Be Basis)	
Magnesium	.0007 Maximum or 140 ppm (Be Basis)	
Manganese	.0001 Maximum or 20 ppm (Be Basis)	
Nickel	.0002 Maximum or 40 ppm (Be Basis)	
Silicon	.0004 Maximum or 80 ppm (Be Basis)	
Sodium	.0006 Maximum or 120 ppm (Be Basis)	

FORM

Damp crystals

STANDARD PACKAGING:

Polyethylene bags, steel container

MINIMUM ORDER: \$ 200 per item

TERMS: Net 30 Days

F.O.B.: Elmore, Ohio

96PL1SFC.DOC